

TECHNICAL DATA SHEET SOLVENT CEMENT PVC N-40

DESCRIPTION

Special adhesive for the PVC rigid unions. Solvent cement N-40 fulfils the norm CE14814 and CE14680.

PROPERTIES

Colour: Colourless
Smell: Characteristic
Viscosity: 5000-8000 Cp at 20°C
Density: 0,99 gr/cm³
Solid matter: 23% + 1%.

INSTRUCTIONS

Clean the surfaces to be fixed with our cleaner. Cut the tube in right angle and bevel its exterior edge faces in an angle of 15 in order to facilitate the entry in the funnel-shaped one. Remove the adhesive preparation before its application. Then, with a flat brush, apply an uniform coat in axial way to both parts to be fixed, applying a thicker coat in the end of the tube. Join the tube and the funnel-shaped without any movement. Hold the assembly firm during some seconds, until the adhesive is forged. Clean immediately the remaining adhesive. Do not subject the joint to efforts or movements before five minutes. It is not recommended to subject the joint to pressures beyond 1,5 atmospheres, before 24 hours from its fixing.

PRESENTATION

Metalic Bottle:

| | |
|--------------|--------------|
| Tube 125 ml. | 25 units/box |
| Tin 250 ml. | 24 units/box |
| Tin 500 ml. | 24 units/box |
| Tin 1000 ml. | 12 units/box |

Plastic Bottle:

| | |
|--------------|--------------|
| Tin 250 ml. | 24 units/box |
| Tin 500 ml. | 24 units/box |
| Tin 1000 ml. | 12 units/box |

STORAGE

Keep in fresh and dry place. Duration: 24 months

RECOMMENDATIONS OF MANAGEMENT RESIDUES

Recommending for reason at the content of recipient, to deliver this recipient at a management residues person authorized for its destruction or its recuperation, as well as anything element to throw out that it was with contact with this product.

NOTE

The information supplied in this Specification Sheet is of general type following our experience. We cannot take responsibility by an inadequate use of the product.