

TECHNICAL DATA SHEET SCREW FIXER IT143

DESCRIPTION

Screw fixer a single component anaerobic product suitable for threaded metal parts against loosening from shock and vibrations. Product cures spontaneously and rapidly when confined in absence of air between close fitting metal surfaces with small gap fill. Screw fixer seal and blocks all kind of bolt connections. High resistance against vibrations polymerises very fast on a high variety of iron metals. Middle to uninstall.

PROPERTIES OF UNCURED MATERIAL

Nature: Methacrylic resin
Appearance: Blue
Viscosity: 500-800 mPas
Specific gravity: 1,6
Flash point: 110°C

INFORMATION ON POLYMERISATION

The speed of cure will depend on two main factors: kind of materials, ambient temperature. The graph below shows the strength developed with time on some kind of metal. The different materials have been tested according to ISO 10964.
The speed of cure will depend on ambient temperature. The right temperature range of cure is from +20°C to +25°C. Low temperature from +5°C to +20°C reduce speed of reaction, higher temperature will increase the speed.

FEATURES OF CURED PRODUCT

The following data have been referred to test carried out at 22°C, after 24 hours.

| | | |
|----------------------|-----------|----------------|
| Breakaway torque | ISO-10964 | N.m 20/30 |
| Prevail torque | ISO-10964 | N.m 15/25 |
| Temperature strength | °C | -50°C a +150°C |
| Max Gap Fill | mm | 0.15 |

CHEMICAL RESISTANCE

Test method DIN-54454

Breakaway torque % after immersion:

| | T °C | 100 h | 500 h | 1000 h |
|--------------|------|-------|-------|--------|
| Water/Glycol | 85 | 90 | 85 | 80 |
| Brake Fluid | 22 | 95 | 90 | 85 |
| Motor Oil | 125 | 95 | 90 | 90 |
| Acetone | 22 | 100 | 90 | 90 |

GENERAL INFORMATION

For use this product in metal/plastics assembling, the compatibility of materials should be tested. Not recommended for use in oxygen facilities and as sealant for strong basic or oxidising agents. For best performance surfaces should be clean and free of grease. Apply the product on the whole busy surface. Shut completely the parts. This product performs better on push-fit assemblies. On difficult metallic surfaces use the product in combination to the Activator. Shelf life: at least 12 months from +5°C to +28°C. The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others whose methods we have no control. It is the user's responsibility to determine suitability of features of the products related to their own production process and to adopt such precaution for the protection of person against any hazards that may be involved in the handling and use.

PRESENTATION

Bottle 50ml. 10 Units/box

RECOMMENDATIONS OF MANAGEMENT RESIDUES

Recommending for reason at the content of recipient, to deliver this recipient at a management residues person authorized for its destruction or its recuperation, as well as anything element to throw out that it was with contact with this product.

NOTE

The information supplied in this Specification Sheet is of general type following our experience. We cannot take responsibility by an inadequate use of the product.